



# Standard Specification for Viscosity-Graded Asphalt Cement for Use in Pavement Construction<sup>1</sup>

This standard is issued under the fixed designation D3381/D3381M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers asphalt cements graded by viscosity at 60°C [140°F] for use in pavement construction. Three sets of limits are offered in this specification. The purchaser shall specify the applicable table of limits. In the event the purchaser does not specify limits, [Table 1](#) shall apply. For asphalt cements graded by penetration at 25°C [77°F]. See Specification [D946](#). If needed, volume corrections for asphalt cements should be made according to Practice [D4311](#).

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- [D5 Test Method for Penetration of Bituminous Materials](#)
- [D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester](#)
- [D95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation](#)
- [D113 Test Method for Ductility of Bituminous Materials](#)
- [D140 Practice for Sampling Bituminous Materials](#)
- [D946 Specification for Penetration-Graded Asphalt Cement for Use in Pavement Construction](#)
- [D1754 Test Method for Effects of Heat and Air on Asphaltic Materials \(Thin-Film Oven Test\)](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee [D04](#) on Road and Paving Materials and is the direct responsibility of Subcommittee [D04.40](#) on Asphalt Specifications.

Current edition approved Dec. 1, 2009. Published January 2010. Originally approved in 1975. Last previous edition approved in 2009 as D3381 – 09. DOI: 10.1520/D3381\_D3381M-09A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene](#)
- [D2170 Test Method for Kinematic Viscosity of Asphalts \(Bitumens\)](#)
- [D2171 Test Method for Viscosity of Asphalts by Vacuum Capillary Viscometer](#)
- [D2872 Test Method for Effect of Heat and Air on a Moving Film of Asphalt \(Rolling Thin-Film Oven Test\)](#)
- [D4311 Practice for Determining Asphalt Volume Correction to a Base Temperature](#)

## 3. Manufacture

3.1 The asphalt cement shall be prepared from crude petroleum by suitable methods.

## 4. Physical Requirements

4.1 The asphalt cement shall be homogeneous, free from water, and shall not foam when heated to 175°C [350°F].

4.2 The asphalt cements shall conform to the requirements given in [Table 1](#), [Table 2](#), or [Table 3](#), as specified by the purchaser.

## 5. Methods of Sampling and Testing

5.1 Sample and test asphalt cements in accordance with the following methods:

- 5.1.1 *Sampling*—Practice [D140](#).
- 5.1.2 *Water*—Test Method [D95](#).
- 5.1.3 *Viscosity at 60°C [140°F]*—Test Method [D2171](#).
- 5.1.4 *Viscosity at 135°C [275°F]*—Test Method [D2170](#).
- 5.1.5 *Penetration*—Test Method [D5](#).
- 5.1.6 *Flash Point, Cleveland Open Cup*—Test Method [D92](#).
- 5.1.7 *Solubility in Trichloroethylene*—Test Method [D2042](#).
- 5.1.8 *Thin-Film Oven Test*—Test Method [D1754](#) (see [Table 1](#) and [Table 2](#)).
- 5.1.9 *Rolling Thin-Film Oven Test*—Test Method [D2872](#) (see [Table 3](#)).
- 5.1.10 *Ductility*—Test Method [D113](#).

## 6. Keywords

6.1 asphalt cement; bitumen; pavement; viscosity

**TABLE 1 Requirements for Asphalt Cement, Viscosity Graded at 60°C [140°F]**

NOTE 1—Grading based on original asphalt.

Test	Viscosity Grade					
	AC-2.5	AC-5	AC-10	AC-20	AC-30	AC-40
Viscosity, 60°C [140°F], Pa·s	25 ± 5	50 ± 10	100 ± 20	200 ± 40	300 ± 60	400 ± 80
Viscosity, 135°C [275°F], min, mm <sup>2</sup> /s	80	110	150	210	250	300
Penetration, 25°C [77°F], 100 g, 5 s, min	200	120	70	40	30	20
Flash point, Cleveland open cup, min, °C [°F]	165 [325]	175 [350]	220 [425]	230 [450]	230 [450]	230 [450]
Solubility in trichloroethylene, min, %	99.0	99.0	99.0	99.0	99.0	99.0
Tests on residue from thin-film oven test:						
Viscosity, 60°C [140°F], max, Pa·s	125	250	500	1000	1500	2000
Ductility, 25°C [77°F], 5 cm/min, min, cm	100 <sup>A</sup>	100	50	20	15	10

<sup>A</sup> If ductility is less than 100, material will be accepted if ductility at 15°C [60°F] is 100 minimum at a pull rate of 5 cm/min.

**TABLE 2 Requirements for Asphalt Cement Viscosity Graded at 60°C [140°F]**

NOTE 1—Grading based on original asphalt.

NOTE 2—Table 2 specifies asphalts that are less temperature susceptible than those specified by Table 1. Asphalts that meet Table 2 requirements will also meet Table 1 requirements of the same grade.

Test	Viscosity Grade					
	AC-2.5	AC-5	AC-10	AC-20	AC-30	AC-40
Viscosity, 60°C [140°F], Pa·s	25 ± 5	50 ± 10	100 ± 20	200 ± 40	300 ± 60	400 ± 80
Viscosity, 135°C [275°F], min, mm <sup>2</sup> /s	125	175	250	300	350	400
Penetration, 25°C [77°F], 100 g, 5 s, min	220	140	80	60	50	40
Flash point, Cleveland open cup, min, °C [°F]	165 [325]	175 [350]	220 [425]	230 [450]	230 [450]	230 [450]
Solubility in trichloroethylene, min, %	99.0	99.0	99.0	99.0	99.0	99.0
Tests on residue from thin-film oven test:						
Viscosity, 60°C [140°F], max, Pa·s	125	250	500	1000	1500	2000
Ductility, 25°C [77°F], 5 cm/min, min, cm	100 <sup>A</sup>	100	75	50	40	25

<sup>A</sup> If ductility is less than 100, material will be accepted if ductility at 15°C [60°F] is 100 minimum at a pull rate of 5 cm/min.

**TABLE 3 Requirements for Asphalt Cement Viscosity Graded at 60°C [140°F]**

NOTE 1—Grading based on residue from rolling thin-film oven test.

Tests on Residue from Rolling Thin-Film Oven Test: <sup>A</sup>	Viscosity Grade				
	AR-1000	AR-2000	AR-4000	AR-8000	AR-16000
Viscosity, 60°C [140°F], Pa·s	100 ± 25	200 ± 50	400 ± 100	800 ± 200	1600 ± 400
Viscosity, 135°C [275°F], min, mm <sup>2</sup> /s	140	200	275	400	550
Penetration, 25°C [77°F], 100 g, 5 s, min	65	40	25	20	20
% of original penetration, 25°C [77°F], min	...	40	45	50	52
Ductility, 25°C [77°F], 5 cm/min, min, cm	100 <sup>B</sup>	100 <sup>B</sup>	75	75	75
Tests on original asphalt:					
Flash point, Cleveland open cup, min, °C [°F]	205 [400]	220 [425]	225 [440]	230 [450]	240 [460]
Solubility in trichloroethylene, min, %	99.0	99.0	99.0	99.0	99.0

<sup>A</sup> Thin-film oven test may be used but the rolling thin-film oven test shall be the referee method.

<sup>B</sup> If ductility is less than 100, material will be accepted if ductility at 15°C [60°F] is 100 minimum at a pull rate of 5 cm/min.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).